

# **ARBO 2020**

#### **DESCRIPTION**

Arbo 2020 is a unique three - part epoxy sealant, which cures to form a flexible, hard wearing seal with good resistance to traffic loads. Arbo 2020 has good adhesion to concrete, many metals, glass and many other common construction substrates and can be colour matched to most colour requirements



#### FLOOR JOINTS

#### **MAIN APPLICATIONS**

Recommended for sealing floor joints in internal environments e.g. kitchens, food processing areas, retail outlets.

Can be used in the manufacture of pre formed movement joints.

**NB:** Not recommended for use in high movement joints or where prolonged water immersion may occur.

Arbo 2020 should be pre -tested against natural stone before application into floor joints formed in natural stone (Please contact Adshead Ratcliffe Technical Services Department for more information)

## **PACKAGING**

2.0 Litre Set, with a tin for the Base, 150 ml cartridge for the Curing Agent and sachet for the colourizer.

Follower plate

#### **COLOURS**

Grey, Black, Bright Red, Stone, Oatmeal, Maize, Buff, Light Brown Other Colours can be colour matched – please contact Adshead Ratcliffe Technical Services Department for further information.

\*NB: Not available in White due to colour instability.

### STORAGE LIFE

9 months in original unopened packaging stored in a cool, dry place out of direct sunlight

#### APPLICATION INSTRUCTIONS

#### Joint Preparation

The joint surfaces must be clean and free from all contamination. Surfaces should be degreased using the appropriate surface cleaner (contact Adshead Ratcliffe Technical Service Department for further information)

#### Mixing

The ratio of base, curing agent and colourizer controls the performance properties of Arbo 2020 and the product is filled off to an exact mixing ratio. It is vital therefore that the whole contents of the Curing Agent and Colourizer packaging are added to the Base tin. The 3 components must be thoroughly mixed to ensure complete homogeneity and colour dispersion.

#### Application

The usual application method once mixed is to fill the sealant into empty cartridge dispensers using the follower tin supplied with the pack. The cartridge is then placed over the hole in the centre of the plate. Applying steady downward pressure will then fill the cartridge. Insert plunger into the cartridge and the mixed sealant is then ready for application using an Arbo Caulking Gun. The sealant should be extruded firmly into the joint by maintaining an even pressure on the trigger of the gun.

#### Joint Backing

Please use appropriate joint filler, e.g. closed cell polyethylene foam should be used to provide the correct joint depth.

All joint preparation and sealant application should be carried out in accordance with BS8000 Part 16 (British standard for the sealing of joints in buildings)

## Joint Size Suitability

Joint Width

Minimum 6mm

Maximum 25mm (single application); 50 mm (multiple applications)

#### Joint Depth

Minimum 10mm on porous substrates (12mm in floor joints) Minimum 6mm on non porous substrates (12 mm in floor joints) Maximum 25mm

Width: Depth ratio (within above min/max restrictions) 2:1 butt joints 1:1 lap/floor joints

#### **HEALTH AND SAFETY**

Base and Curing Agent require careful handling. Please consult MSDS's for each component before use.





# **ARBO 2020**

## **TECHNICAL DATA**

Typical Shore A Hardness

(cured at 20° C): 55 - 65Work Life (Typical at 20° C):  $1\frac{1}{2} - 2$  hours Application Temperature:  $+5^{\circ}$  C to  $+40^{\circ}$  C

Service Temperature: -20° C to +70° C

Cure Rate (at 20° C): 24 hours. At lower temperatures cure

rate will be extended

Chemical Resistance: Resistant to most dilute acids, alkalis

and vegetable oils. Organic solvents may cause the sealant to swell and

lose adhesion.

UV Resistance: Good

Service Life: 20 years (when used in trafficked

joints or subjected to chemical expo sure, service life may be reduced)

Movement Accommodation: Butt joints (movement in tension and

compression): 10 %. Lap joints (movement in shear): 10 %.

## **ACCESSORIES**

## Cleaners

Arbo Cleaner Type 17 - 1 litre Tin (Xylene based – not suitable for use with plastics or delicate finishes)

Arbo Cleaner 16 – 1 Litre Tin (Alcohol Based)

## Equipment

Bulk Loading Guns Heavy Duty Follower Plates

# **QUANTITY ESTIMATOR**

Joint Size (mm)	Metres per 2.0 Litre Set
6 x 6	55
9 x 6	38
12 x 9	18
20 x 10	10

**Important:** The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.

Arbo sealants are manufactured in the U.K. by Adshead Ratcliffe.